

VINYL SULPHONE DYES	Dyeing Shade		Light		Solubility	Washing		Perspiration				Chlorinate Water	Rubbing	
			AATCC	ISO		Effect	Stain	Acid		Alkali			Dry	Wet
	3%	6%						Effect	Stain	Effect	Stain			
ITOFIX YELLOW GL 150% (YELLOW 37)			5	5	150	5	5	5	5	5	5	3-4	5	5
ITOFIX YELLOW GR 150% (YELLOW 15)			5	5	150	5	4-5	5	5	5	5	2-3	5	5
ITOFIX ORANGE 3R (ORANGE 16)			3-4	3-4	100	4	4	4-5	4	3-4	3-4	3	5	3-4
ITOFIX RED 3B			4	4	120	4-5	4-5	4-5	4	4	3-4	3-4	5	3-4
ITOFIX RED RB			4	4	150	4-5	4-5	4-5	4	4	3-4	3-4	5	3-4
ITOFIX RED 7B			4	4	120	4-5	4-5	4-5	3-4	4	3-4	3-4	5	3-4
ITOFIX RED BB 150% (RED 21)			3-4	4	100	4	4	4-5	3-4	4	3-4	2	5	3-4
ITOFIX TURQUOISE BLUE GN 266% (BLUE 21)			5	5	100	4-5	4	5	4-5	5	4	2	5	3-4
ITOFIX BLUE BB 133% (BLUE 220)			4	4	100	4	4	4	4	4	3-4	3	4	3
ITOFIX BLUE R CONC (BLUE 19)			5-6	5-6	150	5	5	4/5	5	4/5	5	3	5	3-4

