

BLACK DYES	Dyeing Shade		Light		Solubility	Washing		Perspiration				Chlorinate Water	Rubbing	
			AATCC	ISO		Effect	Stain	Acid		Alkali			Dry	Wet
	3%	6%						Effect	Stain	Effect	Stain			
ITOFIX NAVY BLUE SGG			4	4	150	4-5	4	5	4	4-5	4	2-3	4-5	2-3
ITOFIX BLACK ANN			4-5	4	100	4-5	4-5	5	4	4-5	4	2	4	2-3
ITOFIX BLACK B 150% (BLACK 5)			4-5	4	100	4-5	4	5	4	5	4	2	4	2-3
ITOFIX BLACK FN			4	4	100	4-5	4	5	4	5	4	2-3	4	2-3
ITOZOL BLACK WM			4	4	100	4-5	4	4-5	4	4-5	4	2-3	4-5	2-3
ITOFIX BLACK GDR-N			4-5	4	100	4-5	4	5	4	5	4	2-3	4	2-3
ITOFIX BLACK GXG			4	4-5	100	4-5	4	5	4	5	4	2-3	4	2-3
ITOFIX BLACK SNG			4	4	100	4-5	4-5	5	4	4-5	4	2-3	4-5	2-3
ITOFIX BLACK SNN			4	4	100	4-5	4	5	4	5	4	2-3	4	2-3

